

Stable Braid[†] - Polyester Double Braid

A firm polyester double braided rope with high strength, low stretch and excellent resistance to wear.

Features

- Torque-free construction
- Durable
- Excellent abrasion resistance
- High resistance to UV degradation
- Spliceable
- High wear and heat resistance
- Excellent flex-fatigue service life
- Firm flexibility
- Low working elongation

Applications

- Winch Lines
- Secondary mooring lines
- Non-HMPE tug lines
- Pulling and stringing lines
- Rodeo/rigging/utility
- Heavy lift slings
- Material hauling lines



SPECIFICATIONS

- Standard colour : White
- Other colours available upon request

Diameter		kg per 100m	lbs per 100ft	Average Strength		Minimum Strength	
(mm)	(in)			(kg)	(lbs)	(kg)	(lbs)
3,2	1/4	3,1	2,1	1 000	2 300	890	2 000
7,9	5/16	4,8	3,2	1 600	3 600	1 400	3 100
9,5	3/8	6,7	4,5	2 500	5 600	2 200	4 800
11,1	7/16	9,1	6,1	3 500	7 700	3 000	6 500
12,7	1/2	12,2	8,2	4 700	10 400	4 000	8 800
14,3	9/16	16,4	11,0	6 000	13 300	5 100	11 300
15,9	5/8	20,8	14,0	7 400	16 300	6 300	13 900
19,1	3/4	26,8	18,0	9 300	20 400	7 900	17 300
22,2	7/8	40,3	27,1	13 600	29 900	11 500	25 400
25,4	1	50,6	34,0	17 800	39 200	15 100	33 300
28,6	1-1/8	67,4	45,3	21 900	48 200	18 600	41 000
31,8	1-1/4	80,2	53,9	26 000	57 300	22 100	48 700
33,3	1-5/16	90,5	60,8	29 300	64 700	24 900	55 000
38,1	1-1/2	109	73,3	34 100	75 100	29 000	63 800
41,3	1-5/8	128	85,9	39 600	87 200	33 600	74 100
44,5	1-3/4	155	104	47 200	104 000	40 100	88 400
50,8	2	185	124	56 200	124 000	47 800	105 000

Elastic Elongation at % break strength

10%	20%	30%
1,10% elongation	1,70% elongation	2,70% elongation

Barry Cordage Ltd.

6110 boul. des Grandes Prairies
Montreal QC H1P 1A2 Canada
☎ 514.328.3888 📠 514.328.1963
1.800.305.2673 (Canada / USA)